

Material Datasheet

Recycled Compound

KRA70N-NAT - A natural medium MFI Impact Modifier from recycled SEBS Compound from post-industrial sources meeting necessary standards for use in manufacturing.

PLASgran Recycled Compounds are **high quality** compounded polymers produced from controlled recycled materials, to **defined specifications**.



Property	Test Methods	Test Conditions	Typical Values	Unit
Melt Flow Index	ISO 1133	2.16kg / 230°C	14	g/10 min
Density	ISO 1133		0.950	g/cm ³
Flexural Modulus	ISO 178	10mm / min	450	MPa
Tensile Stress @ Yield	ISO 527-1,-2	50mm / min	13	MPa
Tensile Elongation @ Break	ISO 8986-2	50mm / min	>200	%
Colour	Visual Inspection		Natural	

Additional Information	Options
Packaging Types Available	25Kg Bag
	Bulk Bag
	Bulk Tanker
	Octabins

****NB**** The property details shown above are typical of the material type and are for guidance only. They do not constitute specification limits. Variances from the above information may occur and no guarantee can be provided or implied due to the factors that may or will influence the processing of the material and varied material sources to produce the material. The above information does not relieve the processor(s), user(s) and product manufacturer(s) of the requirement to carry out their own specific testing.